



Veechem Industries (Pvt.) Ltd

FAVOPRINT ECO FRIENDLY TEXTILE PIGMENTS

30g/kg

1:9



Favoprint L.Yellow AF-GN



Favoprint Yellow AF-2GN



Favoprint Yellow AF-3GN



Favoprint G.Yellow AF-GRP



Favoprint G.Yellow AF-GK



Favoprint Orange AF-R

S.D 1/1 (gm/kg)	CLINO		Fastness to light ISO 105 B02 for 24hrs		Fastness to Dry cleaning ISO 105 D01		Fastness to Chlorine ISO 105 E03 100ppm		Fastness to Hypochlorite bleach ISO 105 N01		Fastness to PVC ISO 105 X10		Heat stability ISO 105 P01 for 1min @ 180C		Stability in discharge (80g/kg. Koolgalt)		Oeko Tex Standard 100 (MAK Amines limit ppm)	

30	Y-12	5-6	4-5	3-4	2-3	4-5	4	4	4	4	4	4	4	•	•		
----	------	-----	-----	-----	-----	-----	---	---	---	---	---	---	---	---	---	--	--

30	Y-14	6	5	4-5	4	4-5	4	4	4	4	4	4-5	•	•		
----	------	---	---	-----	---	-----	---	---	---	---	---	-----	---	---	--	--

30	Y-17	7	6	4-5	4-5	5	4-5	4-5	4-5	3	4-5	•	•			
----	------	---	---	-----	-----	---	-----	-----	-----	---	-----	---	---	--	--	--

30	Y-83	7-8	6-7	4-5	4-5	4-5	4	4-5	4	4	4-5	•	•			
----	------	-----	-----	-----	-----	-----	---	-----	---	---	-----	---	---	--	--	--

30	N.D	6	4-5	2-3	2	4	4	4	3-4	3	4	•	•			
----	-----	---	-----	-----	---	---	---	---	-----	---	---	---	---	--	--	--

30	O-13	6	5	3	2-3	4-5	4	4	4	3-4	4-5	•	•			
----	------	---	---	---	-----	-----	---	---	---	-----	-----	---	---	--	--	--



Veechem Industries (Pvt.) Ltd

FAVOPRINT ECO FRIENDLY TEXTILE PIGMENTS

30g/kg

1:9



Favoprint Orange AF-GS



Favoprint Red AF-GR



Favoprint Red AF-BLN



Favoprint Red AF-RC



Favoprint Red AF-YCS



Favoprint Red AF-GC

S.D 1/1 (gm/kg)	CLINO								Oeko Tex Standard 100 (MAK Amines limit ppm)
	Fastness to light ISO 105 BO2 for 24hrs								
	1/1	1/9	1/1	1/9	1/1	1/9	1/1	1/1	
	Fastness to Dry cleaning ISO 105 DO1								
	1/1	1/9	1/1	1/9	1/1	1/9	1/1	1/1	
	Fastness to Chlorine ISO 105 E03 100ppm								
	1/1	1/9	1/1	1/9	1/1	1/9	1/1	1/1	
	Fastness to Hypo-chlorite Bleach ISO 105 M01								
	1/1	1/9	1/1	1/9	1/1	1/9	1/1	1/1	
Fastness to PVC ISO 105 I01									
1/1	1/9	1/1	1/9	1/1	1/9	1/1	1/1		
Heat stability ISO 105 P01 for limit @ 180C									
Stability in discharge (80g/kg Rongalit)									

30	O-34	7-8	5-6	3-4	3	4-5	4	4	4	4	4-5	•	•
----	------	-----	-----	-----	---	-----	---	---	---	---	-----	---	---

30	N.D	6-7	4-5	4	4	4-5	4	4	4	3-4	4-5	•	•
----	-----	-----	-----	---	---	-----	---	---	---	-----	-----	---	---

30	R-119	7	5-6	4	4	4	4	4	3-4	3-4	4-5	•	•
----	-------	---	-----	---	---	---	---	---	-----	-----	-----	---	---

30	R-146	7	6	4	4	4	3-4	4-5	4	3	4-5	•	•
----	-------	---	---	---	---	---	-----	-----	---	---	-----	---	---

30	N.D	6	5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	•	•
----	-----	---	---	-----	-----	-----	-----	-----	-----	---	-----	---	---

30	R-170	6	4	4	4	4-5	4-5	4-5	4	4-5	4-5	•	•
----	-------	---	---	---	---	-----	-----	-----	---	-----	-----	---	---



Veechem Industries (Pvt.) Ltd

FAVOPRINT ECO FRIENDLY TEXTILE PIGMENTS

30g/kg

1:9



Favoprint Pink AF-5BN



Favoprint Pink AF-3BL



Favoprint Violet AF-RT



Favoprint Violet AF-RSN



Favoprint Violet AF-HS



Favoprint Blue AF-FR

S.D 1/1 (gms/kg)	CLINO	Fastness to light ISO 105 B02 for 24hrs		Fastness to Dry cleaning ISO 105 D01		Fastness to Chlorine ISO 105 E03 100ppm		Fastness to Hypochlorite bleach ISO 105 N01		Fastness to PVC ISO 105 X10		Heat stability ISO 105 P01 for 1min @ 180C		Solubility in discharge (80g/kg Rongalit)	Oeko Tex Standard 100 (MAX Azines limit ppm)
		1/1	1/9	1/1	1/9	1/1	1/9	1/1	1/9	1/1	1/1	1/1	1/1		

30	R-238	5	4	4	4	4	3-4	4	4	2-3	4-5	•	•
----	-------	---	---	---	---	---	-----	---	---	-----	-----	---	---

30	R-122	7	6-7	4-5	4-5	4	4	1-2	1-2	4	4-5	•	•
----	-------	---	-----	-----	-----	---	---	-----	-----	---	-----	---	---

30	V-23	7-8	7	4-5	4	4-5	4-5	4-5	4	4	4-5	•	•
----	------	-----	---	-----	---	-----	-----	-----	---	---	-----	---	---

30	mix	6	5-6	4	3-4	4-5	4	4	4	3-4	4-5	•	•
----	-----	---	-----	---	-----	-----	---	---	---	-----	-----	---	---

30	V-23	7-8	7	4-5	4	4-5	4-5	4-5	4-5	4	4-5	•	•
----	------	-----	---	-----	---	-----	-----	-----	-----	---	-----	---	---

30	B-15	7	6-7	4-5	4	4-5	4	4	4	4	4-5	•	•
----	------	---	-----	-----	---	-----	---	---	---	---	-----	---	---



Veechem Industries (Pvt.) Ltd

FAVOPRINT ECO FRIENDLY TEXTILE PIGMENTS

30g/kg

1:9



Favoprint Blue AF-RS



Favoprint Turq Blue AF-RG



Favoprint Turq Blue AF-RN



Favoprint Green AF-G2B



Favoprint Black AF-BB



Favoprint Black AF-SP

S.D 1/1 (gsm/kg)	CLNO	Fastness to light ISO 105 B01 for 24hrs		Fastness to Dry cleaning ISO 105 D01		Fastness to Chlorine ISO 105 E03 100ppm		Fastness to Hypochlorite bleach ISO 105 N01		Fastness to PVC ISO 105 X10		Heat stability ISO 105 P01 for 1min @ 180°C		Suitability in discharge (80g/kg, Rungali)	Oeko Tex Standard 100 (MAK Amness limit ppm)
		1/1	1/9	1/1	1/9	1/1	1/9	1/1	1/9	1/1	1/1	1/1	1/1		

30	B-15	7	6-7	4	3-4	4-5	4	4	4	4	4	4-5	•	•
----	------	---	-----	---	-----	-----	---	---	---	---	---	-----	---	---

30	B-153	7	6-7	4-5	4	4-5	4	4	4-5	4	4-5	4-5	•	•
----	-------	---	-----	-----	---	-----	---	---	-----	---	-----	-----	---	---

30	B-153	7	6-7	4	4	4-5	4	4	4-5	4	4-5	4-5	•	•
----	-------	---	-----	---	---	-----	---	---	-----	---	-----	-----	---	---

30	GR-7	7-8	7	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	•	•
----	------	-----	---	-----	-----	-----	-----	-----	-----	---	-----	-----	---	---

60	BL-7	7-8	7	4-5	4-5	4-5	4-5	4-5	4-5	4-5	5	5	•	•
----	------	-----	---	-----	-----	-----	-----	-----	-----	-----	---	---	---	---

60	BL-7	7-8	7	4-5	4-5	4-5	4-5	4-5	4-5	4-5	5	5	•	•
----	------	-----	---	-----	-----	-----	-----	-----	-----	-----	---	---	---	---